DESCRIPTION

FLEXE EPG-Stain free epoxy grout recommended for all wet areas and where Hygine is most priority such as Swimming pool, Kitchens, Bathroom, Hospitals, Laboratories, Commercial shops, Mall, Sump, Watertanks, Restroom, Schools, Cafeterias, Covered Terrace etc.



MIXING RATIO \

Part A (Resin: 2 Part) Part B (Hardener: 1 Part) Part C (Filler Powder: 8 Part) Filler powder ratio will be vary based on the workable consistency.

PACKAGING:

5 kg unit & 1 kg unit

SHELF LIFE

For hardner & resin factory sealed containers of this product are guaranteed for one 1 year if stored dry area. For filler powder 24 months from date of packing.

DESCRIPTION

Sanded Cementitious Grout it is Specially designed for wider tile joints 3mm to 12mm, carefully selected graded silica sand, Premium Rubber Polymer Additives and graded pigment will provide water tight, smooth and color consistent grout for your tiles. it resists Crack free joints for your tiles.



MIXING

Factory Sealed containers of this product are guaranteed for 1 years if stored dry area


PACKAGE

10 Kg Bag


SHELF LIFE:

Factory Sealed containers of this product are guaranteed for 1 years if stored dry area

FLEXE EPG GROUT INSTALLATION GUIDE



Clean grout joints



Add two part, Part A Resin and One Part B Hardner



Gradually add EPG Filler Power workable consistency like 8 part of part c Filler Powder



Mix Grout for 5 minutes throughly with properly combined all parts A, B and C



Wait for 2-3 minutes



Re-mix the Grout again at least 2 minutes with out adding any additional liquid



Apply Grout with Float or Putty Plate



Grout from surface



Wait for firm Joints



Lightly Clean off excess Grout with damp sponge or scrubber



Wait for 10 minutes



Remove Haze with Cheesecloth or Turkey towel (White Color)



Wait 24 hrs for Foot traffic



Wait 3 days and make and wait 72 hrs for Heavy Final cleaning using Soap oil hefore continues Traffic

Mobile: +91 7010007117 / 9344600693

eMail: info@flexecrete.com

Web: www.flexecrete.com

FLEXECRETE INDIA PVT LTD.

Factory & Office:

No. 91/3, Pillaiyar Kovil Street, Pandur Village, Kannivakkam, Guduvanchery - 603 202.









