

FLEXE SBR PLUS

MULTIPURPOSE BONDING AGENTS FOR CONCRETE AND MORTAR



SLURRY BOND COAT / WATERPROOFING SLURRY / FOR MORTAR AND SCREEDS

- Mix 1.5 volume of cement to FLEXE SBR PLUS by weight of cement.
- Mix to a lump-free creamy, consistency for 2-3 minutes by slowly adding of FLEXE SBR PLUS
- As water proofing slurry: Mix 2 parts cement to 1 part FLEXE SBR PLUS by weight of cement.
- For Repair Mortar: 1 Litre of FLEXE SBR PLUS and 5kg of Cement:15 kg of sieved sand and 1 litres of water.
- Using a stiff brush, work the bonding slurry well into the damp surface. When the bond coat is tacky apply mortar/screed overlay
- For Floor Topping/Screed. 1 Litre of FLEXE SBR PLUS 5Kg of Cement: 7.5Kg of sand and 7.5 kg of coarse aggregate small size less than 6mm and 1 litres of water.

Mixing Process Mortar/Screed:

- Use lump free cement, well graded sand/aggregates free of excessive fines. Mix sand, cement and coarse aggregate into mixer for 1-2 minutes. Hand mixing is only permissible when the total weight of the mix is less than 23kg.
- Mix required quantity of Flexe SBR Plus and water for 2 minutes in a separate container, to avoid excessive air entrapment.
- Finally, without delay, add the liquid mix slowly into the mixer containing the mixed powdered sand/coarse aggregate and cement until the required consistency is achieved.
- Vertical surfaces: Apply the bonding slurry to the prepared surface and then apply the FLEXE SBR PLUS render onto the wet bonding slurry. Application Thickness: 5 to 25mm.
- Screeds and toppings, applied to horizontal surfaces : Application thickness 10mm to 40mm. The FLEXE SBR PLUS modified mix should be placed over the still wet bonding slurry, well compacted by hand and trowelled to finish using a wooden float or steel trowel.

Packaging:

- 1 Litre
- 5 Litre
- 20 Litre



MANUFACTURED & PACKED BY:
FLEXECRETE INDIA PRIVATE LIMITED.,
No.91/3, Pillaiyar Kovil Street, Pandur Village, Kannivakkam,
Guduvanchery - 603202. Tamil Nadu, India.
Customer Care : +91 9344600693
e-mail: info@flexecrete.com, Web: www.flexecrete.com

FLEXE SBR PLUS

MULTIPURPOSE BONDING AGENTS FOR CONCRETE AND MORTAR




DIRECTION FOR USE



Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae.



Saw cut the concrete areas to a square or rectangular profile to a minimum 10mm depth at the extreme edges. Roughen the surface free of loose particles and dust and saturate with water. Remove excess/standing water.



Where breaking out is not required, roughen the surface and remove any laitance by light scabbling or grit-blasting.

ADVANTAGES

- ✓ Improved tensile and flexural properties
- ✓ Excellent bond to concrete, masonry,
- ✓ Excellent bonds to Old and New concrete
- ✓ Excellent resistant to freeze/thaw
- ✓ Single product multipurpose uses for concrete cement mortars
- ✓ Ideal solution for concrete and mortar repair and patch works
- ✓ Ideal for making floor screeds in internal and external
- ✓ Increase excellent workability and good durable surfaces
- ✓ User friendly